



# Product Information Sheet

## DYNA-PURGE® E2

### *Designed for High-Temperature Engineering Resins*

**DYNA-PURGE E2** delivers the most advanced technology breakthrough in heat stability with enhanced cleaning. Its unique integrated polymer system is engineered for purging high-temperature resins safely and efficiently, under rigorous process conditions.

<b>Applications:</b>	<b>Injection-</b> cold and hot runners <b>Extrusion-</b> profile, sheet & compounding
<b>Temperature Range:</b>	575° F - 715° F (302° C - 379° C)
<b>Types of Resins:</b>	High-temperature engineering resins
<b>Minimum Clearance:</b>	None
<b>Amount of Purge:</b>	1 to 2 times barrel capacity (actual amount needed depends upon machine conditions)

#### FEATURES & BENEFITS:

- Designed for purging high-temperature engineering resins such as PEEK, PEI, PPS, PPA, PSU, etc.
- Engineered for color changes, resin changes, preventative machine maintenance, and prior to manual cleaning
- Effective through a broad temperature range 575° F - 715° F (302° C - 379° C)
- Non-abrasive, non-chemical integrated polymer system thoroughly loosens carbonized and degraded resin, allowing it to be flushed away
- Safe, non-hazardous, ingredients are FDA compliant
- Heat stable- recommended during shutdown and start-up
- Economical- low “cost-per-purge”- only small quantity needed to be effective
- Easy to use- no mixing or soaking required
- Unlimited shelf life

For over 35 years, Dyna-Purge has delivered superior cleaning and economic value over in-house methods and other commercial products. We invite you to sample Dyna-Purge at no-charge, and start saving today!

***Please refer to “Suggested Purging Procedures” for processing information and “Product Selection Guide” for additional products.***

Important! The information presented herein, while not guaranteed, was prepared by competent technical personnel and is true to the best of our knowledge. NO WARRANTY OR GUARANTY, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SUITABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling or storage. Other factors may involve other or additional safety or performance considerations. While our technical personnel can respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State or local laws.