



Product Information Sheet

DYNA-PURGE® SF

Designed for Profile, Sheet, Blown & Cast Film

DYNA-PURGE SF is a non-abrasive, non-chemical engineered thermoplastic purging compound with a proprietary additive, which allows the purge to expand and scrub the screw and barrel, die, and other downstream equipment. The material is designed for extruders and co-extruders that have limited clearances related to screenpacks, mixing or metering devices, etc., when processing profile, sheet, blown and cast film.

Applications:	Extrusion- profile, sheet, blown & cast film
Temperature Range:	320° F - 575° F (160° C - 302° C)
Types of Resins:	All
Minimum Clearance:	None
Amount of Purge:	1 to 2 times barrel capacity (actual amount needed depends on machine conditions)

FEATURES & BENEFITS:

- Excellent for color changes, resin changes, preventative machine maintenance, and before manual cleaning
- Ideal for use when screen packs can't be removed from the extruder
- Effective through a wide temperature range 320° F - 575° F (160° C - 302° C)
- Easy to use- no process adjustment necessary- use at the resident resin processing temperature and RPM speed
- Non-abrasive thermoplastic, which thoroughly loosens carbonized and degraded resin, allowing it to be flushed out of the system
- Safe, non-hazardous, with no chemicals- ingredients are FDA compliant
- Heat stable- recommended during shutdown and start-up
- Low "cost-per-purge"- only small quantity needed to be effective
- No mixing required- simply use "as is"
- Unlimited shelf life

Dyna-Purge has been the top-performing purging compound for over 30 years! Our product line offers superior cleaning and economic value over in-house resins and other commercial purges. We invite you to sample Dyna-Purge at no charge, so you can start saving today!

Please refer to "Suggested Purging Procedures" for processing information and "Grade Selection Guide" regarding additional products.

Important! The information presented herein, while not guaranteed, was prepared by competent technical personnel and is true to the best of our knowledge. NO WARRANTY OR GUARANTY, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SUITABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling or storage. Other factors may involve other or additional safety or performance considerations. While our technical personnel can respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State or local laws.